

222 Cavalcade Street, 77009-3213  
P.O. Box 8768, Houston, Texas 77249-8768  
Tel: (713) 692-9151 Fax: (713) 696-6205

Attention: Grady Smith

**SCAFFOLDMART**

234 Dudley Street  
Greenville, NC 27858  
P: (252) 756-3862 / F: 252/756-3849

W/O. No.: SCA021-12-11-50572-4  
P.O. No.: Grady  
Report Date: 12/18/2008

**Identification:** 5/16" Self Tapping Screws  
**Qty:** 2

**TENSILE TEST RESULTS**

**Specification:** Per Client  
**Direction:** Longitudinal  
**Original Gage Length (in.):** 1.0

Specimen Identification	Diameter, Thread (in.)	Area (sq. in.)	Total Load (lbs)	Tensile Strength, (psi)
Requirement	---	---	---	---
1-1	0.308-18	0.051	8,416	165,000
1-2	0.308-18	0.051	8,792	172,400

**HARDNESS TEST RESULTS**


**Specification:** Per Client  
**Procedure:** ASTM A370 / ASTM E18

Specimen Identification	Hardness Scale	Test #1	Test #2	Test #3	Average
1-1	HRC	37.9	36.0	37.3	37.1
1-2	HRC	37.9	37.1	37.0	37.3

Samples tested for information only.

Unless otherwise noted all test methods and specifications are to the most current revision. Our letters and reports are for the exclusive use of the client to whom they are addressed and shall not be reproduced except in full without the approval of the testing laboratory. The use of our name must receive our written approval. Our letters and reports apply only to the sample tested and/or inspected, and are not indicative of the quantities of apparently identical or similar products. Material submitted to our metals department will be discarded after a period of 30 days unless otherwise directed.

**Respectfully Submitted:**



Ashish Jain  
Manager – Product Evaluation

Stork SWL is an operating unit of Stork Materials Technology B.V., Amsterdam, The Netherlands, which is a member of the Stork group