

222 Cavalcade Street, 77009-3213
P.O. Box 8768, Houston, Texas 77249-8768
Tel: (713) 692-9151 Fax: (713) 696-6205

Attention: Grady Smith

Ureco

1705 S. Evans Street
Greenville, NC 27834
P: 252-756-3862 / F: 252/756-3849

W/O. No.: URE004-09-08-94079-1
P.O. No.: Chemistry
Report Date: 10/3/2005

Chemical Analysis

6'6" x 5' WALK THROUGH FRAME, ITEM #371
Material Identification AISI 1008

Element		Result %	Min %	Max %
C	=	0.05	0.00	0.10
Mn	=	0.43	0.30	0.50
P	=	0.022	0.000	0.040
S	=	0.013	0.000	0.050

5'X5' MASON FRAME, ITEM #377
Material Identification AISI 1020


Element		Result %	Min %	Max %
C	=	0.18	0.18	0.23
Mn	=	0.51	0.30	0.60
P	=	0.014	0.000	0.040
S	=	0.018	0.000	0.050

SIDE BRACKET, ITEM #373
Material Identification AISI 1010

Element		Result %	Min %	Max %
C	=	0.09	0.08	0.10
Mn	=	0.43	0.30	0.60
P	=	0.012	0.000	0.040
S	=	0.019	0.000	0.050

Our letters and reports are for the exclusive use of the client to whom they are addressed and shall not be reproduced except in full without the approval of the testing laboratory. The use of our name must receive our written approval. Our letters and reports apply only to the sample tested and/or inspected, and are not indicative of the quantities of apparently identical or similar products. Material submitted to our metals department will be discarded after a period of 30 days unless otherwise directed.

Respectfully Submitted


Terry Wilt
Manager, Product Evaluation

Stork SWL, is an operating unit of Stork Materials Technology B.V., Amsterdam, The Netherlands, which is a member of the Stork group